

## MEMBRANE PROBING SYSTEM

## ABSTRACT

Sub C 27

5 A substrate, preferably constructed of a ductile material and a tool having the desired shape of the resulting device for contacting contact pads on a test device is brought into contact with the substrate. The tool is preferably constructed of a material that is harder than the substrate so that a depression can be readily made therein. A dielectric (insulative) layer, 10 that is preferably patterned, is supported by the substrate. A conductive material is located within the depressions and then preferably lapped to remove excess from the top surface of the dielectric layer and to provide a flat overall surface. A trace is patterned on 15 the dielectric layer and the conductive material. A polyimide layer is then preferably patterned over the entire surface. The substrate is then removed by any suitable process.

20

c:\...klr\cmi\050\membprob.pat

F0666-1351160